
SURGICRYL® PGA

POLYGLYCOLIC ACID



Type	Monofilament – USP 9/0 – 10/0 Braided and coated multifilament – USP 5/0 – 8/0
Composition	Polyglycolic acid
Coating	Polycaprolactone and calcium stearate (1%)
Colour	Violet / Beige - undyed
Tissue reaction	Minimal
Absorption	The hydrolytic action by which the material is broken down results in total absorption in approximately 60 to 90 days. Approximately 50% of tensile strength remain after 21 days.
Presentation	Box with 12 sutures

For quality & safety

www.sutures.be

SURGICRYL® PGA
POLYGLYCOLIC ACID

CHARACTERISTICS

☑ High tensile strength	Excellent tissue support
☑ Synthetic	Minimal tissue reaction
☑ Breaks down by hydrolysis	Predictable absorption rate
☑ Braided structure	Excellent handling properties High flexibility High tensile strength Excellent knot security
☑ Coated multifilament	Soft passage through the tissues with minimal sawing, tissue drag and trauma Good knot tie down / adjustability Reduced capillary action
☑ Hermetically sealed packing	Guaranteed seal and product sterility

BENEFITS

INDICATIONS General soft tissue closing and/or ligation


especially in
- General surgery
- Skin closure
- Gastrointestinal surgery
- Gynaecology
- Obstetrics
- Plastic surgery
- Urology
- Ophthalmic surgery
- Orthopaedics

CONTRAINDICATIONS
- Cardiovascular surgery
- Neurosurgery


Being absorbable not to use when an extended wound support is required.

Caution in patients with delayed wound healing (e.g. compromised immune system).

TENSILE STRENGTH



ABSORPTION



SURGICRYL® PGA
POLYGLYCOLIC ACID

Side cutting spatula double armed

		Metric	USP	Length		Order number
1/2 circle	2 x HSP 8 mm 200 µm	0.5	7/0	45 cm	violet	OSU07
	2 x HSP 8 mm 300 µm	0.7	6/0	45 cm	violet	OSU061

Side cutting spatula double armed

		Metric	USP	Length		Order number
3/8 circle	2 x DSP 6 mm 200 µm	0.4	8/0	30 cm	violet	OSU08-30
		0.4	8/0	45 cm	violet	OSU08
	2 x DSP 6.2 mm 150 µm	0.2	10/0	30 cm	violet	OSU10
	2 x DSP 6.4 mm 200 µm	0.3	9/0	30 cm	violet	OSU09
		0.5	7/0	45 cm	violet	OSU072
	2 x DSP 8 mm 200 µm	0.5	7/0	45 cm	violet	OSU071

Side cutting spatula

		Metric	USP	Length		Order number
3/8 circle	DSP 6.2 mm 150 µm	0.2	10/0	10 cm	violet	OSU101
	DSP 6.4 mm 200 µm	0.3	9/0	30 cm	violet	OSU09-1

Side cutting spatula double armed

		Metric	USP	Length		Order number
1/4 circle	2 x VSP 8 mm 300 µm 350 µm	0.7	6/0	45 cm	violet	OSU06
		1	5/0	45 cm	violet	OSU05

Micro needle taper point double armed

		Metric	USP	Length		Order number
3/8 circle	MDR 6.4 mm 150µm	0.3	9/0	30 cm	violet	OSU095

SURGICRYL® PGA
POLYGLYCOLIC ACID

Reverse cutting		Metric	USP	Length		Order number
3/8 circle 	DS 12 mm 	0.7	6/0	45 cm	*violet*	11071512
		1	5/0	45 cm	*violet*	11101512
	DS 12 mm Easy Pass 	0.7	6/0	50 cm	*undyed*	11071512UP
		1	5/0	50 cm	*undyed*	11101512UP